



# ZINC-X

## CORROSION INHIBITOR



### FEATURES

- Zinc rich, galvanized primer for rust and corrosion protection
- Inhibits rust on steel through galvanic protection
- >99 % zinc purity
- Dries in 10 to 15 minutes
- Meets or exceeds ASTM A-780-93A
- VOC Compliant
- Withstands water temperature up to 212°F (100°C) and continuous dry heat up to 750°F (400°C)
- Easily removed with common paint thinners (i.e. acetone, xylene, toluene, etc.)

### APPLICATIONS

- Auto & Truck Bodies
- Exhaust Stacks, Mufflers & Manifolds
- Fences
- Heating & Air Conditioning Equipment
- Hot Dip Galvanizing Repair
- Metal Roofs & Gutters
- Offshore Drilling Equipment
- Overseas Storage or Shipments
- Pipes and Water Tanks
- Weldments



### PACKAGE

Net Fill  
14 oz. (397 grams) aerosol

Part No.  
05616

### PROPERTIES

Appearance/Physical State:  
Medium Gray Coating

Evaporation Rate:  
<1

Flash Point:  
<80.6°F (27°C) TCC

Non-Volatiles:  
43%

Propellant:  
Isobutane/Propane

Specific Gravity (water=1):  
2.2 – 2.4

V.O.C. Content:  
32%, 288 g/L, 2.4 lbs./gal

Two coats of Zinc-X can inhibit rust on steel submerged in salt water for up to 6 months.

**Value Performance**

MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE : [WWW.LPSLABS.COM](http://WWW.LPSLABS.COM)

LPS Laboratories • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

Internet Web Site: [www.lpslabs.com](http://www.lpslabs.com)

©2009 LPS Laboratories • LPS® is a registered trademark of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2197 • Rev. 1/2009