



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE	TRADE NAME
ANTI EC 70	Economic oil resistant sheet 70 ShA

POLYMER: NBR/SBR	APPLICATION Oil resistant
---------------------	------------------------------

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	70	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	5	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	200	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	15	min.
ABRASION RESISTANCE	mm ³	DIN 53516		
SPECIFIC GRAVITY	g/cm ³	DIN 53479	1,55	± 0,03

AGEING	Δ H	Sh.A3		5
In: Air	Δ CR	%	ASTM D 573	- 20
For: 72 h	Δ AR	%		- 30
At: 70 °C	Δ V	%		

AGEING	Δ H	Sh.A3		5
In: IRM 901	Δ CR	%	ASTM D 471	
For: 72 h	Δ AR	%		
At: 23 °C	Δ V	%		- 5

AGEING	Δ H	Sh.A3		-10
In: IRM 903	Δ CR	%	ASTM D 471	
For: 72 h	Δ AR	%		
At: 23 °C	Δ V	%		+ 10

WORKING TEMPERATURES							
In Air	°C	ASTM D 573	min:	- 20	max:	+ 70	
In Oil	°C	ASTM D 471	min:		max:	+23	
In Water	°C	ASTM D 471	min:		max:	+80	

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD/POOR	GOOD/POOR	UNSUITABLE	POOR	POOR	POOR

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.