



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE
1532 Bianca

TRADE NAME
Oil resistant white sheet food conta

POLYMER:
NBR

Oil resistant

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	60	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	10	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	450	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	22	min.
ABRASION RESISTANCE	mm ³	DIN 53516		
SPECIFIC GRAVITY	g/cm ³	DIN 53479	1,30	± 0,03

AGEING In: Air For: 72 h At: 70 °C	Δ H	Sh.A3		8	
	Δ CR	%	ASTM D 573	- 20	
	Δ AR	%		- 40	
	Δ V	%			
AGEING In: IRM 901 For: 72 h At: 100 °C	Δ H	Sh.A3		10	
	Δ CR	%	ASTM D 471		
	Δ AR	%			
	Δ V	%		- 10	
AGEING In: IRM 903 For: 72 h At: 100 °C	Δ H	Sh.A3		-10	
	Δ CR	%	ASTM D 471		
	Δ AR	%			
	Δ V	%		+ 10	

WORKING TEMPERATURES					
In Air	°C	ASTM D 573	min:	- 20	max: + 100
In Oil	°C	ASTM D 471	min:		max: +100
In Water	°C	ASTM D 471	min:		max: +90

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD	GOOD	POOR	POOR	GOOD	POOR

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.